

# Northstar International

Bitumen is supplied according to N.I.O.C. specification and special grade bitumen such as MC 120 and MC 250 is available subject to prior approval.

Below are quality levels of regular bitumen:

## **Bitumen Specifications:**

Grade	85-100	60-70
Specific Gravity at 15.6 C	1.03	1.04
Flash Point (min) C	230	240
Softening Point (R&B) C	44-52	49-58
Ductility at 25 C (CM) Min	100	100
Solubility in CC 14%wt (Min)	99.0	99.0
Loss on heating %wt Max (5 hours, 163c)	0.3	0.5
Penetration of residue after loss on heating % of the original Value (Min)	75	75

**FOB or C&F, TERMS AND PROCEDURE available on request**